

GEOMET® 321

The world's choice for corrosion protection

GEOMET® 321 is applied to protect fasteners and many types of metallic parts from corrosion and is used in many industries. It can be combined with PLUS®, DACROLUB® or GEOKOTE® topcoats to provide a very broad range of friction coefficients. It is the most widely used product in zinc flake technology.

- Thin dry-film, non-electrolytic
- Water-based chemistry
- Passivated zinc and aluminium flakes in a binder, patented chemistry
- Chrome free alternative to DACROMET® 320
- Metallic silver appearance

Characteristics and performance*

- The coefficient of friction can be adjusted to targeted values ranging from 0.06 to 0.20 (ISO 16047) with NOF METAL COATING GROUP's selected topcoats
- It can be used with or without topcoat
- No hydrogen embrittlement
- Excellent assembly and multi-tightening behavior (with lubricated topcoat)
- Good mechanical damage (test method D24 1312, USCAR 32) and chemical resistance to VDA 621-412 test
- Performance maintained at elevated temperatures (up to 300°C)
- Paintable coating
- Electrical conductivity for most application processes
- Bimetallic compatibility with aluminum

High corrosion resistance*

Coating Weight	Salt Spray Test (ISO 9227/ASTM B117)	Cyclic Test
> 24 g/m ²	> 240 hours without white rust > 720 hours without red rust	
> 24 g/m ² + topcoat	> 720 hours without red rust	4 cycles ACT 60 cycles GMW 14872 60 cycles SAE J2334
> 36 g/m ²	> 1000 hours without red rust	

* Results may vary depending on substrate, geometry of parts and type of application processes



**NOF METAL COATINGS
GROUP**



GEOMET® 321

Application process

GEOMET® 321 can be applied by Dip-Spin, Spray, Dip-Drain-Spin using bulk or rack

Health and Safety

- Aqueous dispersion
- Complies with REACH
- Complies with the 2011/65/EU and (EU) 2015/863 directives

Among our worldwide specifications

- BMW (GS 90010)
- CHRYSLER (PS-5873, PS-9666)
- DAIMLER (DBL 9440)
- FIAT (Capitolato 9.57513)
- FORD (S438)
- GENERAL MOTORS (GMW3359-GMW14)
- IVECO (18-1101)
- PORSCHE (PTL 7539)
- RENAULT (01-71-002)
- RENAULT Trucks (01-71-4002)
- VOLKSWAGEN (TL245)
- VOLVO Cars (VCS 5737,29)
- ALSTOM (DTRF 150213)
- BOMBARDIER (BT/CE-WN30-02)
- CATERPILLAR (1E1675G)
- JOHN DEERE (JDM F13)
- KNORR BREMSE (N12005)

International standards

EN ISO 10683 - Fasteners: non-electrolytic zinc flake coatings

EN 13858 - Non-electrolytic zinc flake coatings on iron and steel parts

ASTM F1136 / F1136 M - Zinc/Aluminum Corrosion Protective Coatings for Fasteners

